RG104 E-1 Box 121

1880

Weekly Report of Gold Deposits Melted at United States Mint.

Date.	Assay No.	Name of Depositor.	Weight before Melting. OZ.	DEC.	Weight after Melting. OZ.	DEC.	Loss. OZ.	DEC.	Loss per ct.		Gain. OZ.	DEC.	Description of Bullion.
April 5th	595	G. C. Thompson	20	70	19	73		97	4	62			Aml & Lps, N. C.
	6	Do	18	36	18	35		01		06			Button
	7	Do	61	32	50	99	10	33	15	93			Jewelry
	8	W. H. Lee	68	52	68	46		06		09			Bar
	9	Thos R. Lee	107	54	107	49		05		05			Bar
	600	Geo. H. Smith	10	74	10	68		06		55			Button, N. C.
	1	Do	5	75	5	74		01		17			Do
6th	2	G. C. Thompson	34	85	23	07	11	78	33	66			Jewelry Witch Cases
	3	Do	7	68	6	95		73	9	12			Aml, Geo.
	4	Geo. Cohen	14	28	12	75	1	53	10	93			Jewelry, Witch Cases, &c.
	5	Simons, Bro. & Co.	18	07	12	12	5	95	33	06			King, Base
	6	Harry Murray Remelt 29.25	29	33	29	25		08		28			Bar
	7	A. Loudon Snowden, Supt. Remelt 784.15	784	10	784	10							Bars, U. S. M., Denver
8th	8	G. C. Thompson	3	02	2	87		15	5	00			Aml.
	9	Do	10	44	8	92	1	52	15	20			King, Base
	10	Do	20	36	19	30	1	06	5	30			Jewelry Witch Cases
	1	Do	10	75	9	52	1	23	11	18			King, Base
	2	Hagstoy & Thorpe	108	43	108	42		01		009			Bar
	3	Phillips & Jacobs	53	73	53	73							U. S. Coin
	4	John Stuertz	7	12	6	45		67	9	57			Button
	5	Wm Rutter	12	60	10	01	2	59	19	92			Leaf
9th	6	Drexel & Co.	16	55	16	54		01		06			For. Coin
	7	Jas. Mason	3	57	3	57							Do
	8	Wm Simpson, Sons & Co.	6	91	6	78		13	1	86			Aml & Grs, Geo.
10th	9	J. W. Bancroft	14	77	13	16	1	61	10	73			Aml, Geo.
	20	J. C. White	10	79	10	55		24	2	08			D Fl, & Fillings
	1	H. Muhr's Sons	17	60	17	60							Bars
			1477	88	1437	10	40	78	6	59			

Notes of Melter & Refiner. 17/4/80

The deposits are from the following sources:

N. Carolina (2)	3
Georgia	3
Colorado Mnt (1)	1
Finer bullion (3)	6
Base bullion	11
Coin	3
Total	27

The loss in melting the amalg. of Georgia, 9.92 % is unusually full; that of the mixt metal of N. Carolina 4 5/8 % is full enough; that of the same from Georgia, 1 7/8 %, is very low. The loss on the finer bullion, 0.15 %, is very moderate; on the baser bullion, 14.71 %, is a fair average. The loss on coin, only 0.01 oz. on one of the 3 deposits is equivalent to no loss, which is too low.

J. H. Booth
M & R

For week ending April 10th 1880
Approximate value, $ 22,275.05

To the Director of the Mint.

J. Robley Dunglison

Register.

RG104 E-1 Box 121

Report of Gold Deposits
melted for week ending
April 10th 1880

NARA RG104, Entry 1, Box 121

[Abstract:] Report of Gold Deposits melted for week ending April 10, 1880

Weekly Report of Gold Deposits Melted at United States Mint.

[Please see original images for data table.]